








Part Number: **T400-26D**

Revision 20190524 - Generated 2019-May-30



OD	(nom. - bare core) (max. - after coating)	101.60 mm 102.36 mm	4.000 in 4.030 in
ID	(nom. - bare core) (min. - after coating)	57.15 mm 56.39 mm	2.250 in 2.220 in
Ht	(nom. - bare core) (max. - after coating)	33.02 mm 33.78 mm	1.300 in 1.330 in
Mass	(approximate)	1,200 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	6.85 cm ²	
	L _e - Eff. Mag. Path Length	25.0 cm	
	V _e - Eff. Core Volume	171 cm ³	
	WA - Min. Eff. Window Area	25.0 cm ²	
	sa - Surface Area	360 cm ²	
	mlt - mean length per turn	14.2 cm	
Inductance	μ _i (reference)	75	
	A _L value (nominal)	262 nH/N ²	
	Test Winding	N=100, #20 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	3.0 V	
A _L tolerance	±10%		
Core Loss	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$		
	where B _{pk} expressed in gauss, f expressed in hertz, and: a=1.00E+09, b=1.10E+08, c=1.90E+06, d=1.90E-13		
	B _{pk}	140 G	
	frequency	100 kHz	
	Core Loss (nominal)	83 mW/cm ³	
Core Loss (maximum)	95 mW/cm ³		
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and: a=1.00E-02, b=9.70E-06, c=1.72, d=0.00		
	H _{DC}	50 Oe	
	Percent Initial Perm(nom.)	55.2%	
Percent Initial Perm(min.)	47.4%		
Coating/Pkg	Coating Type:	Yellow/White Epoxy Paint	
	Voltage Breakdown (min.)	500 Vrms, 60Hz	
	Limit	3 mA, 5 s	
	Package Quantity	12 Pcs/Box	



Winding Table	Wire Size	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	Single Layer	Turns	45	57	71	89	112	140	174	218	271	338	422
		Rdc(Ω)	13.1 m	26.4 m	52.3 m	104.3 m	208.8 m	415.1 m	820.5 m	1.6	3.2	6.4	12.7
Full Winding	Turns	131	202	313	485	750	1,161	1,797	2,781	4,304	6,662	10,312	
	Rdc(Ω)	38.2 m	93.6 m	230.7 m	568.6 m	1.4	3.4	8.5	20.9	51.3	126.4	311.1	